



Line



Website



On Facebook



On YouTube

產品物性表 (TDS)

● MC212GM20

● 玻纖礦強化級 ● 本色

項目(Item)	測試方法 (Test Method)	單位(Unit)	參考值(Ref. Value)
機械性能(Mechanical)			
衝擊強度	Izod Impact	D-256	23°C Kg-cm/cm - 20°C -40°C
抗張強度	Tensile Str.Yield	D-638	5 — —
伸長率	Tensile Elongation,Break	D-638	Kg/cm ²
抗折強度	Flexural Strength	D-790	%
抗折模數	Flexural Modulus	D-790	Kg/cm ²
硬度	Rockwell Hardness	D-785	R-Scale
800			—
1200			—
50000			—
熱性能(Thermal)			
融點	Melting Point	D-789	°C
熱變形溫度	H.D.T	D-648	°C
線膨脹係數	Coefficient of Thermal Expansion	D-696	E ⁻⁵ 1/°C
66 psi			—
264 psi			195
—			—
—			—
電性測試(Electrical)			
介電強度	Dielectric Strength	D-149	kv/mm
體積電阻	Volume Resistivity	D-257	ohm-cm
耐電弧	Arc Resistance	D-495	Sec
其他(Other)			
比重	Specific Gravity	D-792	--
收縮率	Mold Shrinkage	D-995	%
含水率	Moisture Content	D-570	%
熔融指數	Melt Flow Index	D-1238	23°C,24hr g/10min
灰份含量	Ash Content	--	(270°C/2.16Kg)
—			%
—			'575±25°C · 4hr
耐燃性	Flammability	UL-94	1/8" · 3,18mm 1/16" · 1,59mm 1/32" · 0,79mm
—			HB

附註：

※產品物性和操作條件僅供參考。

※ Product properties and operating conditions are for reference only.

※使用的條件和適用的法規可能隨不同地區或時間而改變，賣方對文件中的資訊不承擔任何義務或法律責任。

※The conditions of use and applicable laws may vary with different regions or times, and the seller does not assume any obligations or legal liabilities in this document.

